



GE Structured Products

LEXAN® 9440 SHEET

Product Data Sheet

INDUSTRIAL

DESCRIPTION

LEXAN® 9440 uncoated polycarbonate sheet is designed to meet the requirements of specialty applications as food handling/contact. LEXAN 9440 sheet complies with FDA food additive regulations (21 CFR 177.1580). LEXAN 9440 sheet offers high impact protection, thermoformability, transparency, and dimensional stability.

TYPICAL PROPERTY VALUES*

Property	Test Method	Units	Value
PHYSICAL			
Specific Gravity	ASTM D792	—	1.20
Light Transmission (Average), 1/8" disk	ASTM D1003	%	88
Water Absorption, Equilibrium, 24 hrs	ASTM D570	%	0.15
@ 73°F			0.35
@ 212°F			0.58
MECHANICAL			
Tensile Strength	ASTM D638	psi	
@ Yield			9,000
Ultimate			9,500
Tensile Modulus	ASTM D638	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Elongation	ASTM D638	%	110
Izod Impact Strength	ASTM D256A	ft-lbs/in	
Notched @ 1/8"			12-16
Unnotched @ 1/8"			60 (no failure)
THERMAL			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75×10^{-5}
Thermal Conductivity	ASTM C177	Btu/hr•ft ² •°F•in	1.35
Heat Deflection Temperature	ASTM D648	°F	
@ 264 psi			270
@ 66 psi			280

LEXAN is a registered trademark of General Electric Company

**These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local GE Plastics Structured Products representative or the GE Plastics Structured Products Quality Services Department.*

DISCLAIMER: THE MATERIALS AND PRODUCTS OF THE BUSINESSES MAKING UP THE GE PLASTICS UNIT OF GENERAL ELECTRIC COMPANY, ITS SUBSIDIARIES AND AFFILIATES, ("GEP") ARE SOLD SUBJECT TO GEP'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, GEP MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING GEP MATERIALS, PRODUCTS, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN GEP'S STANDARD CONDITIONS OF SALE, GEP AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS OR PRODUCTS DESCRIBED HEREIN. EACH USER BEARS FULL RESPONSIBILITY FOR MAKING ITS OWN DETERMINATION AS TO THE SUITABILITY OF GEP'S MATERIALS, PRODUCTS, RECOMMENDATIONS, OR ADVICE FOR ITS OWN PARTICULAR USE. EACH USER MUST IDENTIFY AND PERFORM ALL TESTS AND ANALYSES NECESSARY TO ASSURE THAT ITS FINISHED PARTS INCORPORATING GEP MATERIALS OR PRODUCTS WILL BE SAFE AND SUITABLE FOR USE UNDER END-USE CONDITIONS. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of GEP's Standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by GEP. No statement contained herein concerning a possible or suggested use of any material, product or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of General Electric Company or any of its subsidiaries or affiliates covering such use or design, or as a recommendation for the use of such material, product or design in the infringement of any patent or other intellectual property right.

