

Agilent T-13/4 (5 mm), T-1 (3 mm), Low Current, Double Heterojunction AlGaAs Red LED Lamps

Data Sheet

HLMP-D150/D155, HLMP-K150/K155

Description

These solid state LED lamps utilize newly developed double heterojunction (DH) AlGaAs/GaAs material technology. This LED material has outstanding light output efficiency at very low drive currents. The color is deep red at the dominant wavelength of 637 nanometres. These lamps are ideally suited for use in applications where high light output is required with minimum power output.


Features

- Minimum luminous intensity specified at 1 mA
- · High light output at low currents
- · Wide viewing angle
- Outstanding material efficiency
- · Low power/low forward voltage
- CMOS/MOS compatible
- · TTL compatible
- Deep red color

Applications

- · Low power circuits
- · Battery powered equipment
- Telecommunication indicators

Package Dimensions





NOTES:

1. ALL DIMENSIONS ARE IN MILLIMETRES (INCHES).

2. AN EPOXY MINISCUS MAY EXTEND ABOUT

1 mm (0.040") DOWN THE LEADS.








Selection Guide

		Luminous Intensity Iv (mcd) at 1 mA				Package
					$2\theta_{1/2}^{[1]}$	
Package Description	Device HLMP-	Min.	Тур.	Max.	Degree	Outline
T-1 3/4 Red Tinted Diffused	D150	1.3	3.0	-	65	Α
	D150-C00xx	1.3	3.0	-	65	Α
	D150-CD0xx	1.3	3.0	4.2	65	Α
T-1 3/4 Red Untinted Non-diffused	D155	5.4	10.0	_	24	В
	D155-F00xx	5.4	10.0	_	24	В
T-1 Red Tinted Diffused	K150	1.3	2.0	_	60	С
	K150-C00xx	1.3	2.0	_	60	С
	K150-CD0xx	1.3	3.0	4.2	60	С
T-1 Red Untinted Non-diffused	K155	2.1	3.0	_	45	С
	K155-CD0xx	1.3	3.0	4.2	45	С
	K155-D00xx	2.1	3.0	_	45	С
	K155-DE0xx	2.1	3.0	6.8	45	С

Note:

Part Numbering System



^{1.} $\theta_{1/2}$ is the off axis angle from lamp centerline where the luminous intensity is $^{1}/_{2}$ the on-axis value.

Absolute Maximum Ratings at $T_A = 25^{\circ}C$

Parameter	Value	
Peak Forward Current ^[1]	300 mA	
Average Forward Current	20 mA	
DC Current ^[2]	30 mA	
Power Dissipation	87 mW	
Reverse Voltage (I _R = 100 μA)	5 V	
Transient Forward Current (10 µs Pulse)[3]	500 mA	
LED Junction Temperature	110°C	
Operating Temperature Range	-20 to +100°C	
Storage Temperature Range	-55 to +100°C	
Wave Soldering Temperature [1.59 mm (0.063 in.) from body]	250°C for 3 seconds	
Lead Solder Dipping Temperature [1.59 mm (0.063 in.) from body]	260°C for 5 seconds	

Notes:

- Maximum I_{PEAK} at f = 1 kHz, DF = 6.7%.
 Derate linearly as shown in Figure 4.
- 3. The transient peak current is the maximum non-recurring peak current the device can withstand without damaging the LED die and wire bonds. It is not recommended that the device be operated at peak currents beyond the Absolute Maximum Peak Forward Current.

Electrical/Optical Characteristics at $T_A = 25^{\circ}C$

Symbol	Description	Min.	Тур.	Max.	Unit	Test Condition
$\overline{V_F}$	Forward Voltage		1.6	1.8	V	I _F = 1 mA
$\overline{V_R}$	Reverse Breakdown Voltage	5.0	15.0		V	I _R = 100 μA
λ_{p}	Peak Wavelength		645		nm	Measurement at Peak
$\lambda_{\sf d}$	Dominant Wavelength		637		nm	Note 1
$\Delta \lambda^{1/2}$	Spectral Line Halfwidth		20		nm	
τ_{S}	Speed of Response		30		ns	Exponential Time Constant, e ^{-t} /T _S
С	Capacitance		30		pF	$V_F = 0$, $f = 1 MHz$
$R\theta_{J-PIN}$	Thermal Resistance		260 ^[3] 210 ^[4] 290 ^[5]		°C/W	Junction to Cathode Lead
$\overline{\eta_{V}}$	Luminous Efficacy		80		lm/W	Note 2

Notes:

- $1. \ \ The \ dominant \ wavelength, \ \lambda_{d_r} \ is \ derived \ from \ the \ CIE \ chromaticity \ diagram \ and \ represents \ the \ color \ of \ the \ device.$
- 2. The radiant intensity, I_e , in watts per steradian, may be found from the equation $I_e = I_V/\eta_V$, where I_V is the luminous intensity in candelas and η_V is luminous efficacy in lumens/watt.
- 3. HLMP-D150.
- 4. HLMP-D155.
- 5. HLMP-K150/-K155.




Figure 1. Relative intensity vs. wavelength.




Figure 3. Relative luminous intensity vs. dc forward current.




Figure 2. Forward current vs. forward voltage.




Figure 4. Maximum forward dc current vs. ambient temperature. Derating based on T $_J$ Max. = 110 °C.




Figure 5. Relative luminous intensity vs. angular displacement. HLMP-D150.





Figure 6. Relative luminous intensity vs. angular displacement. HLMP-K150.






Figure 7. Relative luminous intensity vs. angular displacement. HLMP-D155.

Figure 8. Relative luminous intensity vs. angular displacement. HLMP-K155.

Intensity Bin Limits

		Intensity Rar	nge (mcd)
Color	Bin	Min.	Max.
Red	С	1.5	2.4
	D	2.4	3.8
	E	3.8	6.1
	F	6.1	9.7
	G	9.7	15.5
	Н	15.5	24.8
	I	24.8	39.6
	J	39.6	63.4
	K	63.4	101.5
	L	101.5	162.4
	М	162.4	234.6
	N	234.6	340.0
	0	340.0	540.0
	Р	540.0	850.0
	Q	850.0	1200.0
	R	1200.0	1700.0
	S	1700.0	2400.0
	T	2400.0	3400.0
	U	3400.0	4900.0
	V	4900.0	7100.0
	W	7100.0	10200.0
	Χ	10200.0	14800.0
	Υ	14800.0	21400.0
	Z	21400.0	30900.0

Mechanical Option Matrix

Mechanical	
Option Code	Definition
00	Bulk Packaging, minimum increment 500 pcs/bag
01	Tape & Reel, crimped leads, minimum increment 1300 pcs for T-13/4, 1800 pcs for T-1
02	Tape & Reel, straight leads, minimum increment 1300 pcs for T-13/4, 1800 pcs for T-1
A1	T-1, Right Angle Housing, uneven leads, minimum increment 500 pcs/bag
A2	T-1, Right Angle Housing, even leads, minimum increment 500 pcs/bag
B1	T-13/4, Right Angle Housing, uneven leads, minimum increment 500 pcs/bag
B2	T-13/4, Right Angle Housing, even leads, minimum increment 500 pcs/bag
DD	Ammo Pack, straight leads with minimum 2K increment
DH	Ammo Pack, straight leads with minimum 2K increment

Note:

All categories are established for classification of products. Products may not be available in all categories. Please contact your local Agilent representative for further clarification/information.

www.agilent.com/semiconductors

For product information and a complete list of distributors, please go to our web site.

For technical assistance call:

Americas/Canada: +1 (800) 235-0312 or

(916) 788-6763

Europe: +49 (0) 6441 92460 China: 10800 650 0017 Hong Kong: (+65) 6756 2394

India, Australia, New Zealand: (+65) 6755 1939 Japan: (+81 3) 3335-8152 (Domestic/International), or 0120-61-1280 (Domestic Only)

Korea: (+65) 6755 1989

Singapore, Malaysia, Vietnam, Thailand, Philippines, Indonesia: (+65) 6755 2044

Taiwan: (+65) 6755 1843

Data subject to change.
Copyright © 2004 Agilent Technologies, Inc.
Obsoletes 5968-1438EN
November 12, 2004
5988-2229EN

