Overall Width (OW) Opening ATTENTION STATSHIELD® ESD Shielding Bag Metal In Construction Static Sensitive Handling Precautions DescoIndustries.com Length (L) Made in America Lead free RoHS compliant Bag Date & Lot Code Printed for QC Traceablility Weld Weld Width (W Seal

STATSHIELD® METAL-IN SERIES

Specifications:

Standard Document Meets Requirements of: ANSI/ESD S541 (ANSI/ESD S20.20) **ESD Protective Packaging** ANSI/ESD S11.4 Level 3 Technical Requirements

Electrical Properties Typical Values

Surface Resistance: Outer Surface 1×10^4 to $< 1 \times 10^{11}$ ohms ANSI/ESD STM11.11 1×10^4 to $< 1 \times 10^{11}$ ohms Inner Surface ANSI/ESD STM11.11 Discharge Shielding <20 nJ ANSI/ESD STM11.31, EIA 541 Charge Generation Teflon: 0.09 nC/sq. in. Modified Incline Plane Quartz: 0.01 nC/sq. in. Modified Incline Plane

Capacitance Probe (to dissipate 1 KV) <30 volts

ANSI/EIA-541/Appendix E, 1kV Discharge

Test Procedures/Method

Physical Properties

Film Thickness Nominal 0.0030" (0.0762mm) ±10% MIL-STD-3010, 1003

Width (Inside Dimensions) Nominal -0" / + 0.125"

Length (Inside Dimensions) Nominal ± 0.125"

Light Transmission >40% (Tobias) **ASTM D-1003** Heat Seal >10 lbs/in 375°F. 1/2 sec 60 psi Tensile Strength 4600 PSI. 32 MPa **ASTM 882**

Puncture Resistance >10 lbs MIL-STD-3010, 2065 Non-corrosive MIL-STD-3010, M3005 Pass


Silicone Not detected ASTM F168 Marking Adhesion Pass IPC-TM-650 2.4.1

Chemical Properties

Corrosion No effect on aluminum, copper, silver, Sn-Pb coated foil,

stainless steel. low carbon steel

Soft Fold Bottom Side Weld Seals 3/8 in. (±0.10)



Mixed Unsortable Plastic Scrap



Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded,

Protektive Pak bags are recyclable

bonded or laminated together which are unsortable into individual grades.

Statshield® bags are packaged 100 per package in an oversized shielding bag.

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS 2. REACH and Conflict Minerals Statement

None of the RoHS 2 restricted materials, REACH substances of very high concern as of 2015/12/17, or Conflict Minerals are intentionally added in manufacturing this product. Ref. European Union Directive 2011/65/EU and Regulation (EC) No. 1907/2006/CE. See Protektive Pak's Limited Warranty ProtektivePak.com.

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click HERE.

Specifications and procedures subject to change without notice.

STATSHIELD® BAG, SHIELDING, METAL-IN, 0.0030" (0.0762mm)



PROTEKTIVE PAK

13250 MONTE VISTA AVENUE, CHINO, CA 91710 PHONE (909) 627-2578

ProtektivePak.com

DRAWING NUMBER 48700

DATE: June 2016



See Shielding Bag Storage at TB-7057.



United States of America