



# **SPECIFICATION**

(Reference sheet)

• Supplier : Samsung electro-mechanics • Samsung P/N : CL02C3R3CO2GNNC


• Product : Multi-layer Ceramic Capacitor • Description : CAP, 3.3 pF, 16V, ±0.25 pF, C0G, 0100

# A. Samsung Part Number

<u>CL</u> <u>02</u> <u>C</u> <u>3R3</u> <u>C</u> <u>O</u> <u>2</u> <u>G</u> <u>N</u> <u>N</u> <u>C</u> ① ② ③ ④ ⑤ ⑥ ⑦ ⑧ ⑨ ⑩ ⑪

1	Series	Samsung Multi-layer Ceramic Capacitor		
2	Size	01005 (inch code)	L: 0.40 ± 0.02 mm	W: 0.20 ± 0.02 mm
3	Dielectric	C0G	Inner electrode	Cu
4	Capacitance	3.3 pF	Termination	Cu
⑤	Capacitance	±0.25 pF	Plating	Sn 100% (Pb Free)
	tolerance		Product	Normal
6	Rated Voltage	16 V	<b>®</b> Special	Reserved for future use
7	Thickness	$0.20 \pm 0.02 \text{ mm}$	① Packaging	Cardboard type, 7" reel

### B. Structure and dimension



Samsung P/N	Dimension(mm)				
(Lead Free)	L	W	Т	BW	
CL02C3R3CO2GNNC	0.40±0.02	0.20±0.02	0.20±0.02	0.10±0.03	

#### C. Samsung Reliablility Test and Judgement condition

	Performance	Test condition		
Capacitance	Within specified tolerance	1Mb±10% 0.5~5Vrms		
<b>Q</b> 466 min				
Insulation 10,000Mohm or 100Mohm·μF		Rated Voltage 60~120 sec.		
Resistance	Whichever is smaller			
Appearance	No abnormal exterior appearance	Microscope (×20)		
Withstanding No dielectric breakdown or		300% of the rated voltage		
Voltage	mechanical breakdown			
Temperature C0G				
Characterisitcs	From -55℃ to 125℃, Capacitance change should be within ±30PPM/℃)			
Adhesive Strength No peeling shall be occur on the		100g·F, for 10±1 sec.		
of Termination	terminal electrode			
Bending Strength	Capacitance change :	Bending to the limit (1mm)		
	within ±5% or ±0.5pF whichever is larger	with 1.0mm/sec.		
Solderability	More than 75% of terminal surface	SnAg3.0Cu0.5 solder		
	is to be soldered newly	245±5℃, 3±0.3sec.		
		(preheating : 80~120℃ for 10~30sec.)		
Decistores to	Canasitanas shansa	Coldon met 1 270 / 5° 40 / 40 - 5		
Resistance to	Capacitance change :	Solder pot : 270±5℃, 10±1sec.		
Soldering heat	within ±2.5% or ±0.25pF whichever is larger			
Vilentian Test	Tan δ, IR : initial spec.	A more life and a second		
Vibration Test	Capacitance change :	Amplitude: 1.5mm		
	within ±2.5% or ±0.25pF whichever is larger	From 10Hz to 55Hz (return : 1min.)		
Mainton	Tan δ, IR : initial spec.	2hours × 3 direction (x, y, z)		
Moisture	Capacitance change :	With rated voltage		
Resistance	within ±7.5% or ±0.75pF whichever is larger	40±2℃, 90~95%RH, 500+12/-0hrs		
	Q: 111 min			
	IR: 500Mohm or 25Mohm · μF			
Link Townserstone	Whichever is smaller	With 2000/ of the roted valters		
High Temperature	Capacitance change :	With 200% of the rated voltage		
Resistance	within ±3% or ±0.3pF whichever is larger	Max. operating temperature		
	Q: 233 min	1000+48/-0hrs		
	IR: 1,000Mohm or 50Mohm · μF Whichever is smaller			
Tompovotuvo		1 avale condition		
Temperature	Capacitance change :	1 cycle condition		
Cycling	within ±2.5% or ±0.25pF whichever is larger	Min. operating temperature > 25 °C		
	Tan δ, IR : initial spec.	→ Max. operating temperature → 25°C		
		5 cycle test		
	dition can be replaced by the corresponding accelerated test condition			

<sup>\*</sup> The reliability test condition can be replaced by the corresponding accelerated test condition.

# D. Recommended Soldering method:

Reflow (Reflow Peak Temperature: 260+0/-5°C, 10sec. Max)

Product specifications included in the specifications are effective as of March 1, 2013.

Please be advised that they are standard product specifications for reference only.

We may change, modify or discontinue the product specifications without notice at any time.

So, you need to approve the product specifications before placing an order.

Should you have any question regarding the product specifications,

please contact our sales personnel or application engineers.