Versafit

Highly Flame-Retardant, Very Flexible, Low-Shrink-Temperature, Polyolefin Tubing

### **Product Facts**

- 2:1 shrink ratio
- Low shrink temperature reduces installation time and the risk of damage to temperature-sensitive components
- Very flexible; doesn't easily wrinkle when bent
- Highly flame-retardant
- Hot stamps extremely well
- Higher temperature rating, better thermal stability, and higher resistance to physical abuse than noncrosslinked materials
- Free of polybrominated biphenyls (PBBs) and polybrominated biphenyl oxides and ethers (PBBOs and PBBEs), which are classified as environmentally hazardous substances





### **Applications**

Cost-effective choice for many commercial and military applications; electrically insulates and protects in-line components, disconnect terminals, and splices. Bundles wires for very flexible light-duty harnesses. Strain-relieves electrical wire connections for commercial applications. Identifies or color-codes wires, cables, terminals, and components.

#### Installation

Minimum shrink temperature: 70°C [158°F] Minimum full recovery temperature: 90°C [194°F]

### **Operating Temperature Range**

-55°C to 135°C [-67°F to 275°F]

### Specifications/Approvals

| Series   | UL <b>51</b>                | CSA 😘                        | Military                          | Raychem |
|----------|-----------------------------|------------------------------|-----------------------------------|---------|
| Versafit | E35586 VW-1<br>600 V, 125°C | LR31929 VW-1<br>600 V, 125°C | AMS-DTL-23053/5*<br>Classes 1 & 3 | RW-3009 |

<sup>\*</sup>Formerly MIL-I-23053/5 and MIL-DTL-23053/5.



## **Electronics**

# **Single Wall Tubing**

## Raychem

### **Product Dimensions**

### Versafit (Continued)

|       | Inside Di                         | Recovered Wall                     |                                   |  |
|-------|-----------------------------------|------------------------------------|-----------------------------------|--|
| Size  | Minimum Expanded as Supplied      | Maximum Recovered<br>After Heating | Thickness**<br>After Heating      |  |
| 3/64  | $1.63 \pm 0.2 [0.064 \pm 0.008]$  | 0.6 [0.023]                        | $0.40 \pm 0.08 [0.016 \pm 0.003]$ |  |
| 1/16  | 1.85 ± 0.2 [0.073 ± 0.008]        | 0.8 [0.031]                        | 0.43 ± 0.08 [0.017 ± 0.003]       |  |
| 3/32  | 2.79 ± 0.2 [0.110 ± 0.008]        | 1.2 [0.046]                        | 0.51 ± 0.08 [0.020 ± 0.003]       |  |
| 1/8   | $3.43 \pm 0.2 [0.135 \pm 0.008]$  | 1.6 [0.062]                        | 0.51 ± 0.08 [0.020 ± 0.003]       |  |
| 3/16  | 5.21 ± 0.3 [0.205 ± 0.010]        | 2.4 [0.093]                        | 0.51 ± 0.08 [0.020 ± 0.003]       |  |
| 1/4   | 7.11 ± 0.3 [0.280 ± 0.010]        | 3.2 [0.125]                        | 0.64 ± 0.08 [0.025 ± 0.003]       |  |
| 3/8   | 10.16 ± 0.4 [0.400 ± 0.015]       | 4.8 [0.187]                        | 0.64 ± 0.08 [0.025 ± 0.003]       |  |
| 1/2   | 13.72 ± 0.4 [0.540 ± 0.015]       | 6.4 [0.250]                        | 0.64 ± 0.08 [0.025 ± 0.003]       |  |
| 5/8   | 16.90 ± 0.4 [0.665 ± 0.015]       | 8.0 [0.315]                        | $0.76 \pm 0.08 [0.030 \pm 0.003]$ |  |
| 3/4   | 20.45 ± 0.4 [0.805 ± 0.015]       | 9.5 [0.375]                        | $0.76 \pm 0.08 [0.030 \pm 0.003]$ |  |
| 1     | 25.53 ± 0.4 [1.055 ± 0.015]       | 12.7 [0.500]                       | $0.89 \pm 0.12 [0.035 \pm 0.005]$ |  |
| 1 1/4 | 33.40 ± 0.7 [1.315 ± 0.025]       | 15.9 [0.625]                       | 1.02 ± 0.15 [0.040 ± 0.006]       |  |
| 1 1/2 | 39.88 ± 0.8 [1.570 ± 0.030]       | 19.1 [0.750]                       | 1.02 ± 0.15 [0.040 ± 0.006]       |  |
| 2     | 52.83 ± 1.0 [2.080 ± 0.040]       | 25.4 [1.000]                       | 1.14 ± 0.16 [0.045 ± 0.007]       |  |
| 3     | $78.49 \pm 1.0 [3.090 \pm 0.040]$ | 38.1 [1.500]                       | 1.27 ± 0.20 [0.050 ± 0.008]       |  |
| 4     | 104.14 ± 1.3 [4.100 ± 0.050]      | 50.8 [2.000]                       | 1.40 ± 0.23 [0.055 ± 0.009]       |  |

<sup>\*\*</sup>Wall thickness will be less if tubing recovery is restricted during shrinkage.

### **Ordering Information**

| Color  | Standard  | Black (-0), white (-9), red (-2), blue (-6), yellow (-4), green (-5) |  |
|--|---|--|--|
|  | Nonstandard   | Brown (-1), orange (-3), violet (-7), gray (-8)                      |  |
| Size selection   | Always order the largest size that will shrink snugly over the component to be covered. Special order sizes are available upon request. |  |  |
| Standard packaging***  | On spools.  |  |  |
| Ordering description**** Specify product name, size and color (for example, Versafit 1/4-0). |   |  |  |

<sup>\*\*\*</sup>Available in the convenient RaySpool packaging/dispensing system, for sizes 1/16" up to 1".
\*\*\*\*Europe only. For supply to MIL, Def Stan and BS add -MS, -DS or -BS to ordering description.