
#### **RNF-100**

Flexible, Flame-Retardant, General Purpose, Polyolefin Tubing

#### **Product Facts**

- 2:1 shrink ratio
- Superior abrasion and solvent resistance when compared with that of many flexible, general purpose polyolefin tubings
- Excellent physical, chemical, and electrical properties that meet or exceed industrial and military standards for highly reliable, general purpose tubing
- Flexible; conforms to irregular shapes
- Flame-retardant (colors only)
- Wide range of sizes and colors





### **Applications**

Designed to provide superior mechanical (abrasion, cut-through, and strain relief), thermal, and fluid-resistance performance in demanding environments. Widely used to provide insulation and strain relief of wire terminations and connections. Used for jacketing wire bundles and light-duty harnesses where superior abrasion resistance is a plus. Also used to identify and color-code electrical connections and wire bundles.

### Installation

Minimum shrink temperature: 95°C [203°F] Minimum full recovery temperature: 121°C [250°F]

### **Operating Temperature Range**

-55°C to 135°C [-67°F to 275°F]

### Specifications/Approvals

Series	UL <b>'A</b>	CSA 🕦	Military	Industry	Raychem
RNF-100 Type 1 (colors)	E35586 600 V, 125°C	LR31929 600 V, 125°C	AMS-DTL-23053/5*, Class 1 Def. Stan. 59-97 Type 2B	VDE 0341 Pt 9005 Type A and B	RT-350, Type 1 RK-6001
RNF-100 Type 2 (clear)	_	_	AMS-DTL-23053/5*, Class 2 VG 95343 Pt 5 Type B	_	RT-350, Type 2 RK-6001

<sup>\*</sup>Formerly MIL-I-23053/5 and MIL-DTL-23053/5.



### **Electronics**

## Single Wall Tubing

RNF-100 (Continued)

5

# Raychem

 $1.52 \pm 0.23 [0.060 \pm 0.009]$ 

### **Product Dimensions**

	Inside [	Recovered Wall		
Size	Minimum Expanded as Supplied	Maximum Recovered After Heating	Thickness** After Heating	
3/64	1.2 [0.046]	0.6 [0.023]	$0.40 \pm 0.08  [0.016 \pm 0.003]$	
1/16	1.6 [0.063]	0.8 [0.031]	0.43 ± 0.08 [0.017 ± 0.003]	
3/32	2.4 [0.093]	1.2 [0.046]	0.51 ± 0.08 [0.020 ± 0.003]	
1/8	3.2 [0.125]	1.6 [0.062]	0.51 ± 0.08 [0.020 ± 0.003]	
3/16	4.8 [0.187]	2.4 [0.093]	0.51 ± 0.08 [0.020 ± 0.003]	
1/4	6.4 [0.250]	3.2 [0.125]	0.64 ± 0.08 [0.025 ± 0.003]	
3/8	9.5 [0.375]	4.8 [0.187]	0.64 ± 0.08 [0.025 ± 0.003]	
1/2	12.7 [0.500]	6.4 [0.250]	0.64 ± 0.08 [0.025 ± 0.003]	
3/4	19.1 [0.750]	9.5 [0.375]	0.76 ± 0.08 [0.030 ± 0.003]	
1	25.4 [1.000]	12.7 [0.500]	0.89 ± 0.12 [0.035 ± 0.005]	
1 1/4	31.8 [1.250]	15.9 [0.625]	1.02 ± 0.15 [0.040 ± 0.006]	
1 1/2	38.1 [1.500]	19.1 [0.750]	1.02 ± 0.15 [0.040 ± 0.006]	
2	50.8 [2.000]	25.4 [1.000]	1.14 ± 0.16 [0.045 ± 0.007]	
3	76.2 [3.000]	38.1 [1.500]	1.27 ± 0.20 [0.050 ± 0.008]	
4	101.6 [4.000]	50.8 [2.000]	1.40 ± 0.23 [0.055 ± 0.009]	

63.5 [2.500]

### **Ordering Information**

Color	Standard	Plack ( 0. PK) white ( 0. WH) red ( 2. PD) blue ( 6. PH) vellow ( 4. VO)	
Color	Standard	Black (-0, BK), white (-9, WH), red (-2, RD), blue (-6, BU), yellow (-4, YO), green (-5, GN), clear (-X, CL)	
	Nonstandard	Brown (-1, BN), orange (-3, OR), violet (-7, VT), gray (-8, GY)	
Size selection	Always order the largest size that will shrink snugly over the component to be covered. Special order sizes are available upon request		
Standard packaging	On spools or in 1.2-meter [4-foot] lengths.		
Ordering description	Specify product name, size and color (for example, RNF-100 1/4-0 [Europe] or RNF-100 1/4-BK [Americas).		

<sup>\*\*\*</sup>Europe only. For supply to MIL, Def Stan and BS add -MS, -DS or -BS to ordering description.

<sup>127.0 [5.000]</sup> \*\*Wall thickness will be less if tubing recovery is restricted during shrinkage.