


International  
**IR** Rectifier

PD- 91758

**IRG4CC30FB**

IRG4CC30FB IGBT Die in Wafer Form



600 V  
Size 3  
Fast Speed  
6" Wafer

**Electrical Characteristics ( Wafer Form )**

Parameter	Description	Guaranteed (Min/Max)	Test Conditions
$V_{CE(on)}$	Collector-to-Emitter Saturation Voltage	4.5V Max.	$I_C = 10A, T_J = 25^\circ C, V_{GE} = 15V$
$V_{(BR)CES}$	Collector-to-Emitter Breakdown Voltage	600V Min.	$T_J = 25^\circ C, I_{CES} = 250\mu A, V_{GE} = 0V$
$V_{GE(th)}$	Gate Threshold Voltage	3.0V Min., 6.0V Max.	$V_{GE} = V_{CE}, T_J = 25^\circ C, I_C = 250\mu A$
$I_{CES}$	Zero Gate Voltage Collector Current	300 $\mu A$ Max.	$T_J = 25^\circ C, V_{CE} = 600V$
$I_{GES}$	Gate-to-Emitter Leakage Current	$\pm 11\mu A$ Max.	$T_J = 25^\circ C, V_{GE} = +/- 20V$

**Mechanical Data**

Nominal Backmetal Composition, Thickness:	Cr-Ni / V-Ag (1 kA-2kA-2.5kA )
Nominal Front Metal Composition, Thickness:	99% Al, 1% Si (4 microns)
Dimensions:	0.141" x 0.164"
Wafer Diameter:	150mm, with std. < 100 > flat
Wafer thickness:	.015" + / -.003"
Relevant Die Mechanical Dwg. Number	01-5225
Minimum Street Width	100 Microns
Reject Ink Dot Size	0.25mm Diameter Minimum
Ink Dot Location	Consistent throughout same wafer lot
Recommended Storage Environment:	Store in original container, in dessicated nitrogen, with no contamination
Recommended Die Attach Conditions	For optimum electrical results, die attach temperature should not exceed 300C

Reference Standard IR packaged part ( for design ) : IRG4BC30F

**Die Outline**

