

PD - 93867

International IOR Rectifier

IRGC25B120UB


Die in Wafer Form

Features

- GEN5 Non Punch Through (NPT) Technology
- UltraFast
- 10µs Short Circuit Capability
- Square RBSOA
- Positive $V_{CE(on)}$ Temperature Coefficient

Benefits

- Benchmark Efficiency above 20KHz
- Optimized for Welding, UPS, and Induction Heating
- Rugged with UltraFast Performance
- Excellent Current Sharing in Parallel Operation



1200V
 $I_{C(nom)} = 25A$
 $V_{CE(on) typ.} = 3.37V @$
 $I_{C(nom)} @ 25^{\circ}C$
 UltraFast IGBT
 Short Circuit Rated
 150mm Wafer

Electrical Characteristics (Wafer Form)

Parameter	Description	Guaranteed (min, max)	Test Conditions
$V_{CE(on)}$	Collector-to-Emitter Saturation Voltage	2.3V min, 2.7V max	$I_C = 10A, T_J = 25^{\circ}C, V_{GE} = 15V$
$V_{BR(CES)}$	Collector-to-Emitter Breakdown Voltage	1200V min	$T_J = 25^{\circ}C, I_{CES} = 250\mu A, V_{GE} = 0V$
$V_{GE(th)}$	Gate Threshold Voltage	4.4V min, 6.0V max	$V_{GE} = V_{CE}, T_J = 25^{\circ}C, I_C = 250\mu A$
I_{CES}	Zero Gate Voltage Collector Current	10µA max	$T_J = 25^{\circ}C, V_{CE} = 1200V$
I_{GES}	Gate-to-Emitter Leakage Current	$\pm 1.1\mu A$ max	$T_J = 25^{\circ}C, V_{GE} = \pm 20V$

Mechanical Data

Nominal Backmetal Composition, (Thickness)	Al - Ti - Ni/V - Ag, (1kA - 1kA - 4kA - 6kA)
Nominal Front Metal Composition, (Thickness)	99% Al/1% Si, (4µm)
Dimensions	0.257" x 0.260"
Wafer Diameter	150mm, with std. < 100 > flat
Wafer Thickness, Tolerance	185µm, +/-15µm
Relevant Die Mechanical Dwg. Number	01-5376
Minimum Street Width	100µm
Reject Ink Dot Size	0.25mm diameter minimum
Ink Dot Location	Consistent throughout same wafer lot
Recommended Storage Environment	Store in original container, in dessicated nitrogen, with no contamination
Recommended Die Attach Conditions	For optimum electrical results, die attach temperature should not exceed 300°C

Die Outline

