

# Raychem

# TAT-125

Adhesive-Lined, Flexible, Polyolefin Tubing

# Product Facts

- 2:1 shrink ratio
- Thin adhesive lining that bonds to outer tubing and surface below, forming a positive environmental seal
- Flexibility of both tubing and adhesive
- Moisture seal that is resistant to bending of the substrate
- Good mechanical strength and cut-through resistance
- Adhesive that bonds to a wide variety of plastics, rubbers, and metals, including polyethylene, Neoprene<sup>®</sup>, lead, and steel



1	1 Andrews	
	pr	

### Applications

Seals and protects simple in-line splices, bimetallic joints, and components from fluids, moisture, and corrosion. Repairs damaged wire insulation, especially where flexibility is required. Provides onestep electrical insulation and moisture sealing.

#### Installation

Minimum shrink temperature: 95°C [203°F] Minimum full recovery temperature: 121°C [250°F]

#### **Operating Temperature Range**

-55°C to 110°C [-67°F to 230°F]

#### Specifications/Approvals

	Series	UL 🔊	Military	Raychem	
_	TAT-125 Type 1 (colors)	E85381 600 V, 125°C	AMS-DTL-23053/4*, Class 2	TAT-125 SCD	
	TAT-125 Type 2 (clear)	_	_	TAT-125 SCD	-

\*Formerly MIL-I-23053/4 and MIL-DTL-23053/4. Sizes 1/4" through 1 1/2" only.

	Available in:	Americas	Europe	Asia Pacific	
		•		-	
Neoprene is a trademark of E.	I. du Pont de Nemours and Company				3-51
Catalog 1654025	Dimensions are in millimeters	Dimensions are shown for	USA: 1-800-522-6752	South America: 55-11-3611-1514	00.
Revised 12-03	and inches unless otherwise	reference purposes only.	Canada: 1-905-470-4425	Japan: 81-44-900-5102	
www.tycoelectronics.com	specified. Values in brackets are U.S. equivalents.	Specifications subject to change.	Mexico: 01-800-733-8926 C. America: 52-55-5-729-0425	Singapore: 65-4866-151 UK: 44-1793-528171	



# TAT-125 (Continued)

Product	Dime	nsions

	Inside Diameter		Recovered Wall Thickness**	
Size	Minimum Expanded as Supplied	Maximum Recovered After Heating	Total Wall After Heating (Nominal)	Adhesive Wall After Heating (Nominal)
1/8	3.2 [0.125]	1.6 [0.062]	0.69 [0.027]	0.23 [0.009]
3/16	4.8 [0.187]	2.4 [0.093]	0.71 [0.028]	0.25 [0.010]
1/4	6.4 [0.250]	3.2 [0.125]	0.74 [0.029]	0.13 [0.005]
3/8	9.5 [0.375]	4.8 [0.187]	0.74 [0.029]	0.13 [0.005]
1/2	12.7 [0.500]	6.4 [0.250]	0.76 [0.030]	0.15 [0.006]
3/4	19.1 [0.750]	9.5 [0.375]	0.89 [0.035]	0.15 [0.006]
1	25.4 [1.000]	12.7 [0.500]	1.07 [0.042]	0.20 [0.008]
1 1/2	38.1 [1.500]	19.1 [0.750]	1.19 [0.047]	0.28 [0.011]

\*\*Wall thickness will be less if tubing recovery is restricted during shrinkage.

## **Ordering Information**

Color	Standard	dard Black (-0)		
	Nonstandard	White (-9), red (-2), blue (-6), yellow (-4), green (-5), brown (-1), orange (-3), violet (-7), gray (-8), clear (-X , not flame-retardant)		
Size selection	Always order the largest size that will shrink snugly over the component to be covered. Special order sizes are available upon request.			
Standard packaging	In 1.2-meter [4-foot] lengths.			
Ordering description	Specify product name, size and color (for example, TAT-125 1/4-0).			